

# EXPANDED GRAPHITE GASKET SHEETS

## TEMAGRAPH S



## TEMAGRAPH FI



## TEMAGRAPH TI



## TEMAGRAPH NI



## TEMAGRAPH HP





## TEMAGRAPH TG





A comprehensive range of graphite products to cover every application

Temac, a.s. manufacture and distribute a range of graphite sheets designed for demanding fluid sealing applications. The products are manufactured from high purity expanded graphite and are available in a variety of configurations.


Graphite sheets are typically used for sealing against higher temperatures than can be accommodated with CSF (Compressed Synthetic Fibre) materials. When the graphite is reinforced with a metallic insert, they are also capable of sealing against high pressures.




For applications requiring very high levels of tightness, inner and outer metallic eyelets can be fitted to both standard and non-standard shaped gaskets.



Due to the compressible nature of the expanded graphite, large or unusually shaped gaskets can be fabricated from dovetailed segments. The segments interlock and join together under compressive load.




Graphite gaskets can be cut using water jet technology, allowing complex and diverse shapes to be fabricated with minimum waste.



CNC cutting technology is also available for both single and multiple components, including highly complex shapes, producing high levels of accuracy at rapid speed.



## APPLICATION OF TEMAC GRAPHITE GASKETS



**TEMAGRAPH S****TEMAGRAPH FI****PRINTING COLOUR****DESCRIPTION AND APPLICATION****WITHOUT BRANDING**

Temagraph S is a basic sheet made of expanded graphite without reinforcement. This product is also used in the manufacturing of Temagraph materials with stainless steel or nickel foil insertions.



**RED BRANDING**

Temagraph FI is a graphite laminate product reinforced with one or more thin flat metallic insertions which are bonded using a chloride-free adhesive layer. It is general service material for high pressure and high temperature applications including steam. This material is mainly used in chemical, petrochemical and related industries.

|                        |                               |
|------------------------|-------------------------------|
| Marking acc. to        | DIN 28 091-4                  |
| Sheet size             | m                             |
| Thickness              | mm                            |
| No. of insertion       | pc                            |
| Thickness of insertion | mm                            |
| Material of insertion  | DIN / ASTM                    |
| Max. temperature*      | °C                            |
| Max. pressure*         | bar                           |
| Density                | g/cm³                         |
| Compressibility        | ASTM F 36A-66                 |
| Recovery               | ASTM F 36A-66                 |
| Residual stress        | DIN 52 913, 300°C/50MPa N/mm² |
| Tensile strenght       | MPa                           |
| Ash content            | DIN 51 903                    |
| Chloride content       | ppm                           |

|                       |                        |
|-----------------------|------------------------|
| GR-10                 | GR-10-O-1 K Cr         |
| 1,0 x 1,0 (1,5 x 1,5) | 1,0 x 1,0              |
| from 1,0 to 3,0       | from 0,8 to 3,0        |
| without insertion     | 1 and more             |
| –                     | 0,05                   |
| –                     | 1.4404 / SS 316 (flat) |
| from - 200 to +500    | from - 200 to +500     |
| 60                    | 100                    |
| 0,7–1,2               | 0,7–1,0                |
| 45–52                 | 40–50                  |
| 10–15                 | 10–15                  |
| > 47                  | > 45                   |
| > 4                   | unlisted               |
| < 2                   | < 2                    |
| < 50                  | < 50                   |

|                        |
|------------------------|
| GR-10-O-1 K Cr         |
| 1,0 x 1,0              |
| from 0,8 to 3,0        |
| 1 and more             |
| 0,05                   |
| 1.4404 / SS 316 (flat) |
| from - 200 to +500     |
| 100                    |
| 0,7–1,0                |
| 40–50                  |
| 10–15                  |
| > 45                   |
| unlisted               |
| < 2                    |
| < 50                   |



Legend: 1 - suitable subject to chemical compactability  
2 - suitable extended area, technical advice is recommended  
3 - for this area technical consultation is mandatory

\* max. values can not be used simultaneously  
– gasket factors on requested  
– if required the material can be supplied in so-called nuclear grade

**TEMAGRAPH TI****BLUE BRANDING**

Temagraph TI is a graphite laminate product reinforced with one or more tanged metallic insertions. It is designed to be used in demanding applications, providing reliable long term service. Temagraph TI is largely used in flange connections for piping, vessels and other machinery. It is suitable for steam systems and process duties in the chemical, petrochemical, power and manufacturing industries.

**TEMAGRAPH NI**

EASY  
PROCESSING

**GREEN BRANDING**


Temagraph NI is made of high purity, exfoliated graphite reinforced with a flat nickel insertion. It is designed for general applications within the chemical and petrochemical and manufacturing industries. The sheets are easy to handle and to cut.

**TEMAGRAPH HP**

HIGH  
PARAMETERS

**ORANGE BRANDING**

Temagraph HP is high integrity, multilayer sheet material with outstanding mechanical strength. It is designed for higher pressure and temperature applications (up to 200 bar at 500 °C) and for flange connections where resistance to high bolt loadings is required. Temagraph HP is manufactured from the high purity expanded graphite foil reinforced with a number of perforated steel inserts (thickness 0,55mm) without the use of adhesive. This sandwich design confers high compressive strength to the material making it suitable for tongue and groove and exchanger applications as well as variety of demanding applications in the oil, refining and chemical industries. The multilayer composition also ensures that the product adapts well to a variety of flange surfaces.

**TEMAGRAPH TG**

HIGH  
PARAMETERS





**VIOLET BRANDING**

Temagraph TG is high quality, graphite sealing sheet reinforced with an expanded, three-dimensional, stainless steel insert. The unique geometry of the expanded metal insert combined with the excellent sealing properties of the expanded graphite foils, provide the sheet with excellent thermal and mechanical loading capabilities. Temagraph TG is especially suitable for petrochemical, oil, chemical and heating plant industry applications.

|                          |                    |                                      |                            |
|--------------------------|--------------------|--------------------------------------|----------------------------|
| GR-10-O-1 M Cr           | GR-10-I K-Ni       | GR-11-I-3M Cr                        | GR-10-O-1MK- Cr            |
| 1,0 x 1,0 (1,5 x 1,5)    | 1,0x1,0            | 1,0 x 1,0 (1,5 x 1,5)                | 1,5 x 1,5m (1,0 x 1,0)     |
| from 1,0 to 3,0          | from 1,0 to 3,0    | from 1,0 to 4,0                      | from 1,0 to 3,0            |
| 1 and more               | 1                  | 1 and more                           | 1                          |
| 0,1                      | 0,013              | 0,05                                 | 0,15 (Passo 6 mm)          |
| 1.4404 / SS 316 (tanged) | Nikl 2.4066 (flat) | 1.4404 / SS 316 (tanged)             | 1.4301 / SS 304 (expanded) |
| from -200 to +500        | from -200 to +450  | from -200 to +550                    | from -200 to +500          |
| 140                      | 120                | 200                                  | 200                        |
| 1,0                      | 1,0                | 1,1                                  | 1,35                       |
| 30–40                    | 45–50              | $\varepsilon_{KSW}$ (at 20 °C) 30-40 | 40                         |
| 10–15                    | 10–13              | $\varepsilon_{KRW}$ (at 20 °C) 4–5   | 15                         |
| > 48                     | > 45               | $\varepsilon_{WSW}$ (at 300 °C) < 4  | 37 dle BS                  |
| unlisted                 | unlisted           | $\varepsilon_{WRW}$ (at 300C °C) 4–5 | unlisted                   |
| < 2                      | < 2                | < 1                                  | ≤ 2,0                      |
| < 50                     | < 50               | < 25                                 | ≤ 50                       |

|                          |                    |                                      |                            |
|--------------------------|--------------------|--------------------------------------|----------------------------|
| GR-10-O-1 M Cr           | GR-10-I K-Ni       | GR-11-I-3M Cr                        | GR-10-O-1MK- Cr            |
| 1,0 x 1,0 (1,5 x 1,5)    | 1,0x1,0            | 1,0 x 1,0 (1,5 x 1,5)                | 1,5 x 1,5m (1,0 x 1,0)     |
| from 1,0 to 3,0          | from 1,0 to 3,0    | from 1,0 to 4,0                      | from 1,0 to 3,0            |
| 1 and more               | 1                  | 1 and more                           | 1                          |
| 0,1                      | 0,013              | 0,05                                 | 0,15 (Passo 6 mm)          |
| 1.4404 / SS 316 (tanged) | Nikl 2.4066 (flat) | 1.4404 / SS 316 (tanged)             | 1.4301 / SS 304 (expanded) |
| from -200 to +500        | from -200 to +450  | from -200 to +550                    | from -200 to +500          |
| 140                      | 120                | 200                                  | 200                        |
| 1,0                      | 1,0                | 1,1                                  | 1,35                       |
| 30–40                    | 45–50              | $\varepsilon_{KSW}$ (at 20 °C) 30-40 | 40                         |
| 10–15                    | 10–13              | $\varepsilon_{KRW}$ (at 20 °C) 4–5   | 15                         |
| > 48                     | > 45               | $\varepsilon_{WSW}$ (at 300 °C) < 4  | 37 dle BS                  |
| unlisted                 | unlisted           | $\varepsilon_{WRW}$ (at 300C °C) 4–5 | unlisted                   |
| < 2                      | < 2                | < 1                                  | ≤ 2,0                      |
| < 50                     | < 50               | < 25                                 | ≤ 50                       |

|                          |                    |                                      |                            |
|--------------------------|--------------------|--------------------------------------|----------------------------|
| GR-10-O-1 M Cr           | GR-10-I K-Ni       | GR-11-I-3M Cr                        | GR-10-O-1MK- Cr            |
| 1,0 x 1,0 (1,5 x 1,5)    | 1,0x1,0            | 1,0 x 1,0 (1,5 x 1,5)                | 1,5 x 1,5m (1,0 x 1,0)     |
| from 1,0 to 3,0          | from 1,0 to 3,0    | from 1,0 to 4,0                      | from 1,0 to 3,0            |
| 1 and more               | 1                  | 1 and more                           | 1                          |
| 0,1                      | 0,013              | 0,05                                 | 0,15 (Passo 6 mm)          |
| 1.4404 / SS 316 (tanged) | Nikl 2.4066 (flat) | 1.4404 / SS 316 (tanged)             | 1.4301 / SS 304 (expanded) |
| from -200 to +500        | from -200 to +450  | from -200 to +550                    | from -200 to +500          |
| 140                      | 120                | 200                                  | 200                        |
| 1,0                      | 1,0                | 1,1                                  | 1,35                       |
| 30–40                    | 45–50              | $\varepsilon_{KSW}$ (at 20 °C) 30-40 | 40                         |
| 10–15                    | 10–13              | $\varepsilon_{KRW}$ (at 20 °C) 4–5   | 15                         |
| > 48                     | > 45               | $\varepsilon_{WSW}$ (at 300 °C) < 4  | 37 dle BS                  |
| unlisted                 | unlisted           | $\varepsilon_{WRW}$ (at 300C °C) 4–5 | unlisted                   |
| < 2                      | < 2                | < 1                                  | ≤ 2,0                      |
| < 50                     | < 50               | < 25                                 | ≤ 50                       |



## CHEMICAL RESISTANCE TABLE

| TEMAGRAPH                     |   | S | F1 | T1 | N1 | HP                        | TG | TEMAC |
|-------------------------------|---|---|----|----|----|---------------------------|----|-------|
|                               |   | A | A  | A  | A  | A                         | A  | A     |
| Acetic acid 10%               | A | A | A  | A  | A  | A                         | A  | A     |
| Acetone                       | A | A | A  | A  | A  | C                         | C  | C     |
| Acetylene                     | A | A | A  | A  | A  | A                         | A  | A     |
| Adipic acid                   | A | A | A  | A  | A  | A                         | A  | A     |
| Air                           | A | A | A  | A  | A  | A                         | A  | A     |
| Alum                          | A | A | A  | A  | A  | A                         | A  | A     |
| Aluminium chloride            | A | C | C  | C  | C  | C                         | C  | C     |
| Ammonia                       | A | A | A  | A  | A  | C                         | C  | C     |
| Ammonium hydrogenphosphate    | A | A | A  | A  | A  | B                         | B  | B     |
| Ammonium hydroxide            | A | B | B  | B  | B  | A                         | A  | A     |
| Ammonium chloride             | A | A | A  | A  | A  | A                         | A  | A     |
| Aniline                       | A | C | C  | C  | C  | A                         | A  | A     |
| Aqua regia                    | C | C | C  | C  | C  | C                         | C  | C     |
| Asphalt                       | A | A | A  | A  | A  | A                         | A  | A     |
| Barium chloride               | A | A | A  | A  | A  | A                         | A  | A     |
| Benzene                       | A | A | A  | A  | A  | A                         | A  | A     |
| Boric acid                    | A | A | A  | A  | A  | A                         | A  | A     |
| Butane                        | A | A | A  | A  | A  | A                         | B  | B     |
| Butyl alcohol                 | A | A | A  | A  | A  | Oxygen (up to 350 °C)     | A  | A     |
| Calcium hydroxide             | A | B | B  | B  | B  | Paraffin                  | A  | A     |
| Calcium hypochlorite          | A | A | A  | A  | A  | Petrol                    | A  | A     |
| Calcium sulphate              | A | A | A  | A  | A  | Phenol                    | A  | A     |
| Carbon dioxide                | A | A | A  | A  | A  | Phosphoric acid 95%       | A  | A     |
| Carbon disulphide             | A | A | A  | A  | A  | Potassium cyanide         | A  | A     |
| Cooper sulphate               | A | A | A  | A  | A  | Potassium dichromate      | A  | B     |
| Cyclohexanone                 | A | A | A  | A  | A  | Potassium chloride        | A  | B     |
| Cyklhexanone                  | A | A | A  | A  | A  | Potassium iodide          | A  | B     |
| Di-butyl phthalate            | A | A | A  | A  | A  | Potassium nitrate         | A  | B     |
| Ethane                        | A | A | A  | A  | A  | Soap solutions            | A  | B     |
| Ethyl acetate                 | A | A | A  | A  | A  | Sodium carbonate          | A  | B     |
| Ethyl alcohol                 | A | A | A  | A  | A  | Sodium hydrogen carbonate | A  | B     |
| Ethyl ether                   | A | A | A  | A  | A  | Sodium hydroxide          | A  | B     |
| Ethyl chloride                | A | A | A  | A  | A  | Sodium chloride           | A  | B     |
| Ethylene                      | A | A | A  | A  | A  | Sodium sulphate           | A  | B     |
| Ethylene glycol               | A | A | A  | A  | A  | Steam saturated           | A  | B     |
| Fluorine dioxide              | C | C | C  | C  | C  | Sugar                     | A  | B     |
| Fluorine gas                  | B | C | C  | C  | C  | Sulphuric acid 30%        | A  | B     |
| Fluorine liquid               | C | C | C  | C  | C  | Sulphuric acid 70%        | A  | C     |
| Formaldehyde                  | A | A | A  | A  | A  | Sulphurous acid           | A  | C     |
| Fuel aviation                 | A | A | A  | A  | A  | Tartaric acid             | A  | B     |
| Gas LPG                       | A | A | A  | A  | A  | Tetrachlorethane          | A  | B     |
| Gas natural                   | A | A | A  | A  | A  | Tetrachlormethane         | A  | B     |
| Glycerine                     | A | A | A  | A  | A  | Toulene                   | A  | B     |
| Hydrofluoric acid (up to 40%) | B | C | C  | C  | C  | Turpentine                | A  | B     |
| Hydrogen                      | A | A | A  | A  | A  | Vinyl chloride            | A  | B     |
| Hydrogen fluoride             | A | C | C  | C  | C  | Water                     | A  | B     |
| Hydrogen chloride             | A | A | A  | A  | A  | Water chlorinated         | A  | B     |
| Hydrogen chloride dry         | A | A | A  | A  | A  | Water potable             | A  | B     |
| Hydrogen chloride wet         | A | C | C  | C  | C  | Water sea                 | A  | B     |
| Hydrogen peroxide 6%          | B | C | C  | C  | C  | Water waste               | A  | B     |
| Hydrochloric acid 20%         | A | A | A  | A  | A  | Xylene                    | A  | B     |
| Chlorine dry                  | A | A | A  | A  | A  |                           | A  | A     |
| Chlorine water                | C | C | C  | C  | C  |                           | A  | A     |
| Chlorine wet                  | C | C | C  | C  | C  |                           | A  | A     |
| Chlormethane                  | A | A | A  | A  | A  |                           | A  | A     |

A - suitable for application  
 B - suitable depends on conditions  
 C - not suitable

If another medium is applied please contact our technical team.

**Contact:**  
Temac, a.s.  
289 13 Zvěřínek  
Czech Republic

**Sales:**  
Tel.: +420 325 550 246  
+420 325 550 244  
+420 325 550 243  
Fax: +420 325 513 402  
+420 325 550 250  
+420 325 550 284

E-mail:  
sngsales@temac.cz  
eastsales@temac.cz  
export@temac.cz

Web:  
[www.temac.cz](http://www.temac.cz)

**Tech. dept.:**  
Tel.: +420 325 550 181  
Fax: +420 325 550 284

E-mail:  
[tech.help@temac.cz](mailto:tech.help@temac.cz)